

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
5 July 2001 (05.07.2001)

PCT

(10) International Publication Number
WO 01/47843 A1

(51) International Patent Classification⁷: C07C 5/48,
B01J 23/54

Ian, Allan, Beattie [GB/GB]; 12 Crowthorne Close,
Southfields, London SW18 5RX (GB).

(21) International Application Number: PCT/GB00/04813

(74) Agent: CHUNG, Hsu, Min; BP International Limited,
Patents & Agreements, Chertsey Road, Sunbury-on-Thames,
Middlesex TW16 7LN (GB).

(22) International Filing Date:
14 December 2000 (14.12.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
9930597.1 23 December 1999 (23.12.1999) GB
0006387.5 16 March 2000 (16.03.2000) GB

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(71) Applicant (*for all designated States except US*): BP
CHEMICALS LIMITED [GB/GB]; Britannic House, 1
Finsbury Circus, London EC2M 7BA (GB).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): COUVES, John, William [GB/GB]; 4 Orchard Drive, Wooburn Green, High Wycombe, Buckinghamshire HP10 0QN (GB). GRIF-FITHS, David, Charles [GB/GB]; 75 Common Road, Claygate, Esher, Surrey KT10 0HU (GB). MESSENGER, Brian, Edward [GB/GB]; Honeysuckle Cottage, 32 Middle Hill, Englefield Green, Surrey TW20 0JQ (GB). REID,

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 01/47843 A1

(54) Title: PROCESS FOR THE PRODUCTION OF OLEFINS

(57) Abstract: A process for the production of an olefin from a hydrocarbon, which process comprises: partially combusting the hydrocarbon and an oxygen-containing gas in the presence of a catalyst, characterised in that the catalyst comprises palladium and at least one further metal, said further metal being a Group IIIA, Group IVA, VA or a transition metal.

PROCESS FOR THE PRODUCTION OF OLEFINS

The present invention relates to a process for the production of olefins.

Olefins such as ethylene and propylene may be produced by a variety of processes, including the steam cracking of hydrocarbons or by the dehydrogenation of paraffinic feedstocks. More recently, olefins have been produced by a process known as auto-thermal cracking. In such a process, a hydrocarbon feed is mixed with an oxygen-containing gas and contacted with a catalyst. The hydrocarbon feed is partially combusted, and the heat produced is used to drive the dehydrogenation reaction.

An example of an auto-thermal cracking process is described in EP 0 332 289. The patent describes platinum group metals as being capable of supporting combustion beyond the fuel rich limit of flammability. Preferred catalysts are supported platinum catalysts such as platinum/gamma alumina spheres, and platinum/monoliths such as platinum/cordierite or mullite monoliths.

In WO 97/26987, such platinum catalysts are modified with Sn or Cu, in the substantial absence of palladium. According to page 4, lines 32 to 34 of the patent, palladium causes the catalyst to coke up and deactivate very quickly.

We have now found that, contrary to prior art suggestions, compositions comprising palladium are effective as catalysts for auto-thermal cracking processes.

Accordingly, the present invention provides a process for the production of an olefin from a hydrocarbon, which process comprises:

partially combusting the hydrocarbon and an oxygen-containing gas in the presence of a catalyst, characterised in that the catalyst comprises palladium and at least one further metal, said further metal being a Group IIIA, Group IVA, VA, a transition

metal or a lanthanide.

It should be understood that unless otherwise specified, the term "further metal" covers all elements of Group IIIA, IVA, VA, transition metal and lanthanide series of the Periodic Table.

- 5 For the avoidance of doubt, the platinum and at least one further metal in the catalyst may be present in any form, for example, as a metal, or in the form of a metal compound, such as an oxide.

The partial combustion reaction is carried out by contacting a feed comprising the hydrocarbon and a molecular oxygen containing gas with the catalyst. Any suitable
10 oxygen-containing gas may be employed; air being an example.

The preferred stoichiometric ratio of hydrocarbon to oxygen is 5 to 16, preferably, 5 to 13.5 times, more preferably, 6 to 10 times the stoichiometric ratio of hydrocarbon to oxygen required for complete combustion of the hydrocarbon to carbon dioxide and water.

- 15 Preferably, hydrogen is co-fed into the reaction. It is believed that in the presence of the catalyst, hydrogen combusts preferentially relative to the hydrocarbon, thereby increasing the olefin selectivity of the overall process.

Additional feed components such as nitrogen, carbon monoxide and steam may also be fed into the reaction.

- 20 Suitable Group IIIA metals include Al, Ga, In and Tl. Of these, Ga and In are preferred.

Suitable Group IVA metals include Ge, Sn and Pb. Of these, Ge and Sn are preferred.

Suitable Group VA metals include Sb and Bi. Of these, Bi is preferred.

- 25 Suitable metals in the transition metal series are any metal from Group IB to VIIIB of the Periodic Table. In particular, transition metals selected from Groups IB, IIB, VIB, VIIB and VIIIB of the Periodic Table are preferred. Examples of such metals include Cr, Mo, W, Fe, Ru, Os, Co, Rh, Ir, Ni, Pt, Cu, Ag, Au, Zn, Cd and Hg. Preferred transition metals are Mo, Rh, Ru, Ir, Pt, Cu and Zn.

- 30 Suitable lanthanides include lanthanum and cerium.

In one embodiment of the present invention, the catalyst comprises only one metal selected from Group IIIA, Group IVA, VA, the transition metal and lanthanide series.

For example, the catalyst may comprise palladium and one metal selected from the group consisting of Ga, In, Sn, Ge, Sb, Bi, Cu, Ce and La. Palladium may nominally form between 0.01 and 5.0 wt %, preferably, between 0.01 and 2.0 wt %, and more preferably, between 0.05 and 1.0 wt % of the total weight of the catalyst. It should be noted, however, that not all the metal employed during the preparation of the catalyst necessarily becomes incorporated in the catalyst composition. Thus, the actual loading of metal may differ from the nominal loading. To ensure that the desired actual metal concentrations are achieved, the nominal metal concentrations may have to be varied accordingly.

10 The actual loading of palladium may be between 10 and up to 100% of the nominal value. Preferably, the actual loadings are above 40%, more preferably, above 70% (e.g. 90 to 99%) of the nominal values. In a preferred embodiment, the actual loading of palladium is between 0.01 and 5.0 wt %, preferably, between 0.01 and 2.0 wt %, and more preferably, between 0.05 and 1.0 wt % of the total weight of the catalyst.

15 The atomic ratio of palladium to the Group IIIA, IVA, VA, transition or lanthanide metal may be 1 : 0.1 - 50.0, preferably, 1 : 0.1 - 12.0, more preferably, 1 : 0.2 - 3.0, and even more preferably, 1 : 0.5 - 1.5.

Where the metal is a Group IIIA metal, Ga and In are preferred. Atomic ratios of Pd to Ga or In may be 1 : 0.1 to 50, preferably, 1 : 0.1 - 12.0, and more preferably, 1 : 0.5 - 8.0. For example, where the Group IIIA metal is In, the Pd to In ratio may be 1 : 0.7 - 2, for example, 1:1.

Where the metal is a Group IVA metal, Sn and Ge are preferred. Sn is most preferred. Atomic ratios of Pd to Sn or Ge may be 1 : 0.1 to 50, preferably, 1 : 0.1 - 12.0, and more preferably, 1 : 0.5 - 8.0. For example, the Pd:Ge ratio may be 1 : 0.1 to 8, preferably, 1 : 0.5 to 6, for example, 1 : 5.8; 1:1 and 1:0.5. The Pd:Sn ratio may be 1:0.5 - 17. In one embodiment, the atomic ratio of Pd:Sn is 1 : 13 to 17, for example 1 : 15. In another embodiment the atomic ratio of Pd:Sn is 1 : 0.5 to 4.5, for example 1 : 2.5.

Where the metal is a Group VA metal, Sb and Bi are preferred. Atomic ratios of Pd to Sb or Bi may be 1 : 0.1 to 50, preferably, 1 : 0.1 - 12.0, and more preferably, 1 : 0.5 - 8.0.

Where the metal is a transition metal, the metal is preferably Mo, Rh, Ru, Ir, Zn, and more preferably, Cu. Preferred atomic ratios of Pd:Cu are 1 : 0.1 - 3.0, preferably, 1 :

0.2 - 2.0, and more preferably, 1: 0.5 - 1.5, for example, 1:0.8.

Where the metal is a lanthanide, the metal is preferably La or Ce.

In another embodiment, the catalyst comprises at least two metals selected from Group IIIA, Group IVA, VA, the transition metal and lanthanide series. For example, the catalyst may comprise Pd, Pt and Cu, or Pd, Pt and Sn. Palladium may nominally form between 0.01 and 5 wt %, preferably, between 0.01 and 2.0 wt %, and more preferably, 0.05 - 1.0 wt % of the total weight of the catalyst. As described above, the actual loading of metal may differ from the nominal loading. Thus, the actual loading of palladium may be between 10 and up to 100% of the nominal value. Preferably, the actual loadings are above 40%, more preferably, above 70% (eg 90 to 99%) of the nominal values. In a preferred embodiment, the actual loading of palladium is between 0.01 and 5 wt %, preferably, between 0.01 and 2.0 wt %, and more preferably, 0.05 - 1.0 wt % of the total weight of the catalyst.

Where the catalyst comprises at least two metals selected from Group IIIA, Group IVA, VA, the transition metal and lanthanide series, the catalyst preferably comprises a) palladium, b) a further transition metal and c) a Group IIIA or IVA metal. The transition metal (b) is preferably platinum. The metal c) is, preferably, a Group IVA metal, more preferably, Sn or Ge, and most preferably, Sn. The atomic ratio of palladium to metal (b) (e.g. platinum) may be 1: 0.1 - 10.0, preferably, 1: 0.5 - 8.0, and more preferably, 1: 1.0 - 5.0. The atomic ratio of palladium to metal c) may be 1: 0.1 - 60, preferably, 1: 0.1: 50. Thus, where metal c) is Sn, the atomic Pd:Sn ratio may be 1: 0.1 - 60, preferably, 1: 0.1 - 50.0. Atomic Pd: metal c) ratios of 1: 0.1 - 12.0 may also be suitable. For example, where metal c) is Cu, the atomic Pd:Cu ratio is preferably 1: 0.1 - 3.0, more preferably, 1: 0.2 - 2.0, and most preferably, 1: 0.5 - 1.5.

The catalyst may be unsupported. For example, the catalyst may be in the form of a metal gauze. Preferably, however, the catalyst employed in the present process is a supported catalyst. The catalyst may be supported on any suitable support. Ceramic supports are generally preferred, although metal supports may also be employed.

Where ceramic supports are used, the composition of the ceramic support may be any oxide or combination of oxides that is stable at high temperatures of, for example, between 600°C and 1200°C. The support material preferably has a low thermal expansion co-efficient, and is resistant to phase separation at high temperatures.

Suitable ceramic supports include lithium aluminium silicate (LAS), alumina (α - Al_2O_3), yttria stabilised zirconia, alumina titanate, niascon, and calcium zirconyl phosphate. The supports may be wash-coated, for example, with γ - Al_2O_3 .

The structure of the support material is important, as this may affect flow patterns through the catalyst. Such flow patterns may influence the transport of reactants and products to and from the catalyst surface, thereby affecting the catalyst's activity. Preferably, the substrate is a continuous multi-channel ceramic structure, such as a foam, a regular channelled monolith or a fibrous pad. The pores of foam monolith structures tend to provide tortuous paths for reactants and products. Such supports may have 20 to 80, preferably, 30 to 50 pores per inch. Channel monoliths generally have straighter, channel-like pores. These pores are generally smaller, and there may be 80 or more pores per linear inch of catalyst. The support may be in the form of spheres or other granular shapes, or may be present as a thin layer or wash coat on another substrate.

The catalyst employed in the present invention may comprise further elements, such as alkali metals. Suitable alkali metals include lithium, sodium, potassium and caesium.

The catalyst employed in the present invention may be prepared by any method known in the art. For example, gel methods and wet-impregnation techniques may be employed. Typically, the support is impregnated with one or more solutions comprising the metals, dried and then calcined in air. The support may be impregnated in one or more steps. Preferably, multiple impregnation steps are employed. The support is preferably dried and calcined between each impregnation, and then subjected to a final calcination, preferably, in air. The calcined support may then be reduced, for example, by heat treatment in a hydrogen atmosphere.

In the case of a catalyst comprising palladium, platinum and tin, the support material is preferably impregnated in a palladium/platinum solution, and then in a solution comprising tin. Once impregnated, the catalyst is dried at eg 50 to 200°C, and calcined at eg 100 to 700°C, e.g. 300 to 700 between each impregnation. The support is then subjected to a final calcination step at eg 400 to 1500°C in air. The catalyst may then be reduced in, for example, a hydrogen atmosphere. This reduction treatment may be carried out at temperatures of up to 1000°C, for example, 100 to 750 °C.

The catalyst may be in the form of a fluidised or fixed bed. Preferably, a fixed bed

catalyst is employed.

The partial combustion reaction may be suitably carried out at a catalyst exit temperature of between 600°C and 1200°C, preferably between 850°C and 1050°C and most preferably, between 900°C and 1000°C.

5 The reaction may be carried out at atmospheric or elevated pressure. Suitable pressures range from 0 to 2 bara, preferably 1.5 to 2 bara, for example 1.8 bara. Elevated pressures of for example, 2 to 50 bara, may also be suitable.

10 The hydrocarbon may comprise any suitable hydrocarbon. Preferably, gaseous hydrocarbons are employed. Suitable gaseous hydrocarbons include ethane, propane, butane and mixtures thereof.

The hydrocarbon is passed over the catalyst at a gas hourly space velocity of greater than 10,000 h⁻¹, preferably above 20,000 h⁻¹ and most preferably, greater than 100,000 h⁻¹. It will be understood, however, that the optimum gas hourly space time velocity will depend upon the pressure and nature of the feed composition.

15 Advantageously, heat may also be supplied by pre-heating the hydrocarbon. The temperature to which the hydrocarbon, oxygen-containing gas and (optionally) hydrogen mixture may be preheated, however, is limited by the autoignition properties (eg temperature) of the feed.

20 Where the cracking reaction is carried out at elevated pressure, the reaction products may be quenched as they emerge from the reaction chamber to avoid further reactions taking place.

Any coke produced in the process of the present invention may be removed by mechanical means, or using one of the decoking methods described in EP 0 709 446.

25 According to a second aspect of the present invention, there is provided a catalyst comprising a) palladium, b) a further transition metal and c) a metal from Group IIIA, IVA and/or VA.

These and other aspects of the present invention will now be described, by way of example, with reference to Figure 1 of the drawings, which is a schematic view of an apparatus suitable for carrying out an embodiment of the present invention.

30 Figure 1 depicts an apparatus 10 comprising a reactor 12 surrounded by a furnace 14. The reactor 12 may be formed of quartz or metal. Where a metal reactor 12 is employed, the inside of the reactor is lined with quartz (not shown). Typically, metal

reactors are more susceptible to heat loss than quartz reactors.

The reactor 12 is coupled to an oxygen supply 16 and a hydrocarbon feed supply 18. The hydrocarbon feed comprises ethane, and small amounts of hydrogen and nitrogen. A catalyst 20 is located within the reactor 12. The catalyst 20 is placed
5 between a pair of LAS heat shields 22, 24.

The furnace is set to minimise heat losses, and the reactants 16, 18, are introduced into the reactor via line 26. As the reactants contact the catalyst 20, some of the ethane in the hydrocarbon feed 18 combusts to produce water and carbon oxides. The hydrogen co-feed also combusts to produce water. Both these combustion reactions
10 are exothermic, and the heat produced is used to drive the dehydrogenation of ethane to ethylene.

Examples

Example 1 - Preparation of Pd/Pt/Sn Catalyst

The catalyst was prepared by multiple impregnation of a lithium aluminium
15 silicate support having a high purity alumina (HPA) wash-coat. The support was impregnated in 1) a platinum/palladium solution $((\text{NH}_3)_4\text{Pt}^{\text{II}}\text{Cl}_2, (\text{NH}_3)_4\text{Pd}^{\text{II}}\text{Cl}_2)$, and 2) an SnCl_2/HCl solution. Between each impregnation, the support was dried at 120°C , and calcined at 450°C . The catalyst was then calcined in air at 600°C for 6 hours, and then reduced in an atmosphere of hydrogen (1.0nl/min), and nitrogen (1.5 nl/min) for 1 hour
20 (at 700°C).

The catalyst was analysed and found to have 0.36 wt % Pt, 0.04 wt % Pd and 1.85 wt % Sn.

Comparative Example A - 1 wt% Pt

A catalyst having a nominal loading of 1 wt % Pt was prepared by impregnating a
25 lithium aluminium silicate support having an HPA wash-coat in a solution of $(\text{NH}_3)_4\text{Pt}^{\text{II}}\text{Cl}_2$. The impregnated support was dried at 120°C , and calcined at 450°C . The catalyst was then calcined in air at 1200°C for 6 hours. The catalyst was analysed and found to have 0.86 wt% Pt.

Comparative Example B - Pt/Sn

30 A catalyst comprising Pt and Sn was prepared by impregnating a lithium aluminium silicate support having an HPA wash-coat in a solution of 1) $(\text{NH}_3)_4\text{Pt}^{\text{II}}\text{Cl}_2$, and 2) SnCl_2/HCl . The impregnated support was dried, calcined and reduced as

described in connection with Example 1 above. The catalyst was analysed and found to have 0.48 wt % Pt, and 2.80 wt % Sn.

Example 2

The catalysts of Example 1, Comparative Example A and Comparative Example B above were each tested as catalysts for the oxidative dehydrogenation of ethane. Each catalyst was mounted in the apparatus of Figure 1, and an oxidative dehydrogenation reaction was carried out under the conditions summarised in Table 1 below. For the tests below, a metal reactor 12 was employed.

Table 1

	1 (Pd/Pt/Sn)	A (Pt only)	B (Pt/Sn)
GHSV @ stp/h	120863	119759	120268
ethane flow (g/min)	18.07	17.28	18.07
hydrogen flow (g/min)	1.18	1.21	1.18
Oxygen flow (g/min)	9.39	9.68	9.39
nitrogen flow (g/min)	4.95	4.52	4.72

10

As shown in Table 2 below, the selectivity of the catalyst of Example 1 towards ethylene is greater than those of Comparative Examples A and B, respectively.

Table 2

	1 (Pd/Pt/Sn)	A (Pt only)	B (Pt/Sn)
ethane conversion (%)	74.70	75.69	73.03
selectivity (g ethylene per 100g ethane converted)	73.93	67.54	69.7

15

Example 3- Preparation of 0.2 wt %Pd/ 4.0 wt %Sn Catalyst

The catalyst was prepared by multiple impregnation of a lithium aluminium silicate support having an HPA wash-coat. The support was impregnated in 1) a palladium solution ((NH₃)₄Pd^{II}Cl₂), and 2) an SnCl₂/HCl solution. Between each impregnation, the support was dried at 120°C, and calcined at 450°C. The catalyst was

then calcined in air at 600°C for 6 hours, and then reduced in an atmosphere of hydrogen (1.0nl/min), and nitrogen (1.5 nl/min) for 1 hour at 750°C.

The nominal loadings of the resulting catalyst were: 0.2 wt % palladium and 4.0 wt % tin. The catalyst was analysed and found to have 0.19 wt % Pd and 3.18 wt % Sn.

5 **Example 4- Preparation of 1 wt %Pd/ 4.0 wt %Sn Catalyst**

The process of Example 3 was repeated but the concentration of the palladium solution employed was increased such that the nominal loadings of the resulting catalyst were 1 wt % palladium and 4 wt % tin. The catalyst was analysed and found to have 0.98 wt % Pd and 2.70 wt % Sn.

10 **Comparative Example C**

A catalyst having the same composition as Comparative Example B was prepared by impregnating a lithium aluminium silicate support having an HPA wash-coat in a solution of 1) $(\text{NH}_3)_4\text{Pt}^{\text{II}}\text{Cl}_2$, and 2) SnCl_2/HCl . The impregnated support was dried, calcined and reduced as described in connection with Example 1 above. However,
15 instead of being reduced at 700°C, the catalyst of Comparative Example C was reduced at 750°C.

Example 5

The catalysts of Examples 3, 4, and Comparative Examples A and C were each tested as catalysts for the dehydrogenation of ethane. Each catalyst was mounted in the
20 apparatus of Figure 1, and a dehydrogenation reaction was carried out under the conditions summarised in Table 3 below. For the tests below, a quartz reactor 12 was employed. The quartz reactor employed is less susceptible to heat loss than the metal reactor employed, for example, in Example 2. For this reason, the ethylene selectivities obtained using a quartz reactor tend to be higher than those obtained using a metal
25 reactor.

Table 3

	3 (0.2 wt % Pd/4 wt % Sn)	4 (1 wt %Pd/4 wt % Sn)	A (1 wt %Pt only)	C (1 wt % Pt/4 wt %Sn)
GHSV @ stp/h	120864	121073	121073	120864
ethane flow (g/min)	18.94	18.94	18.94	18.94
hydrogen flow (g/min)	1.14	1.14	1.14	1.14
Oxygen flow (g/min)	9.09	9.09	9.09	9.09
nitrogen flow (g/min)	4.95	5.03	5.00	4.95

As shown in Table 4 below, Examples 3 and 4 are more selective towards ethylene than Comparative Example A. Examples 3 and 4 show a similar selectivity to ethylene as Comparative Example C, but at a higher rate of ethylene conversion.

Table 4

	3 (0.2 wt % Pd/4 wt % Sn)	4 (1 wt %Pd/4 wt % Sn)	A (Pt only)	C (Pt/Sn)
ethane conversion (%)	77.75	77.05	73.55	75.67
selectivity (g ethylene per 100g ethane converted)	73.21	73.93	70.65	73.50

Example 6 - Preparation of Pd/Cu catalyst

The catalyst was prepared by multiple impregnation of a lithium aluminium silicate support having an HPA wash-coat. The support was calcined in air to 1200°C for 6 hours prior to impregnation. The support was impregnated in (1) an aqueous palladium solution $(\text{NH}_3)_4\text{Pd}^\text{II}\text{Cl}_2$ and (2) an aqueous copper solution $\text{Cu}(\text{NO}_3)_2$. Between each impregnation the support was dried at 120°C and calcined at 450°C. The catalyst was then calcined at 600°C for 6 hours then reduced in an atmosphere of hydrogen (1.0 nl/min) and nitrogen 91.5 nl/min) at 750°C for 1 hour prior to testing.

The target / nominal loadings of the resulting catalyst were 0.2 wt% palladium and 0.5 wt% copper.

Example 7

The catalyst of Example 6 was tested as a catalyst for the dehydrogenation of ethane using the apparatus of Figure 1. A quartz reactor 12 was employed. The performance of this catalyst was compared to that of three other catalysts: one having Pd, as the only metal component, a second comprising only Pt, and a third catalyst comprising Pt and Cu. The reaction conditions are summarised in Table 5. The ethane conversions and selectivities obtained are summarised in Table 6.

Table 5

	1wt% Pd / 0.5wt% Cu	Pd only	Pt only	Pt/Cu
GHSV @ stp (h)	120864	120482	121073	119948
ethane flow (g/min)	18.94	18.07	18.94	18.07
hydrogen flow (g/min)	1.14	1.18	1.14	1.18
Oxygen flow (g/min)	9.09	9.39	9.09	9.39
nitrogen flow (g/min)	4.95	4.80	5.00	4.60

10

Table 6

	1wt% Pd / 0.5wt% Cu	Pd only	Pt only	Pt/Cu
target (nominal) loadings Pt / Pd / Cu (wt%)	--- / 1.0 / 0.5	--- / 0.2 / ---	1.0 / --- / ---	1.0 / --- / 0.5
ethane conversion (%)	78.17	76.29	73.55	78.00
ethylene selectivity (g per 100g ethane converted)	72.01	69.70	71.44	71.47

Example 8 - Preparation of Pd/Ge catalysts

In this example, Pd/Ge catalysts having the following Pd:Ge atomic ratios were prepared: 1:5.8, 1:1 and 2:1. The nominal Pd:Ge weight % ratios of these catalysts were 1:4, 1:0.74 and 1:0.37, respectively.

- 5 The catalysts were prepared by sequential impregnation of 30ppi ceramic foam blocks (lithium aluminium silicate with alumina washcoat, pre-calcined in air to 1200°C,) with aqueous tetramminepalladium(II) chloride and germanium tetrachloride in ethanol. The foam blocks employed were 15mm in diameter and 30 mm in depth. Between impregnations, the blocks were dried in air at 120-140°C for ca. 30 minutes, calcined in
10 air at 450°C for 30 minutes, and then cooled to room temperature. Once all the impregnation solution had been absorbed onto the foam the blocks were calcined in air at 600°C for 6 hours.

Prior to ATC testing the catalysts were given an *in situ* reduction at 750°C under flowing hydrogen (ca. 1.0 nl/min) and nitrogen (ca. 1.5 nl/min) for 1 hour.

Example 9

15 The catalysts of Example 8, and Comparative Example A were tested as catalysts for the oxidative dehydrogenation of ethane. Each catalyst was mounted in the apparatus of Figure 1, and an oxidative dehydrogenation reaction was carried out under the conditions summarised in Table 7 below.

20

Table 7

	Pd/Ge (atomic ratio Pd:Ge = 1:5.8)	Pd/Ge (atomic ratio Pd:Ge = 1:1)	Pd/Ge (atomic ratio Pd:Ge = 2:1)	A (Pt only)
GHSV @ stp/h	250972	250734	250719	250510
ethane flow (g/min)	8.07	8.07	8.07	8.07
hydrogen flow (g/min)	7.87	7.87	7.87	7.87
Oxygen flow (g/min)	3.94	3.94	3.94	3.94
nitrogen flow (g/min)	2.30	2.27	2.27	2.25

As shown in Table 8 below, the ethylene selectivities of the catalysts of Example 8 were greater than that of Comparative Example A.

Table 6

	Pd/Ge (atomic ratio Pd:Ge = 1:5.8)	Pd/Ge (atomic ratio Pd:Ge =	Pd/Ge (atomic ratio Pd:Ge = 2:1)	A (Pt only)
ethane conversion (%)	76.35	76.74	78.83	78.27
selectivity (g ethylene per 100g ethane converted)	70.05	70.10	69.25	68.57

5 **Example 10 – Preparation of Pd/In catalysts**

In this Example, a Pd/In catalyst having a Pd:In atomic ratio of 1:1 was prepared.

Foam blocks (lithium aluminium silicate (LAS) with an alumina wash-coat (28mm diameter by 30mm deep, 30 pores per inch) were pre-calcined in air at 1200°C to remove porosity/surface area associated with the wash-coat. The blocks were then
10 repeatedly impregnated from an aqueous solution of tetra-amine palladium(II) chloride nitrate and indium(III) nitrate with sufficient salt to give a nominal loading of 2wt% palladium and 2.16wt% indium, assuming 100% absorption of the salt onto the foam. (Corresponding to an atomic palladium:indium ratio of 1:1). Impregnation was carried out alternately from the Pd and In solutions

15 Between impregnations excess solution was removed from the foam blocks and the blocks were dried in air at 120-140°C then calcined in air at 450°C for ca. 30 minutes.

Once all the solutions had been absorbed onto the foams the blocks were dried and given a final air calcination at 600°C for 6 hours.

Example 11

20 The catalyst of Example 10 was loaded into the quartz reactor then given an in-situ hydrogen reduction at 750°C for 1 hour.

The catalyst was then tested as a catalyst for the oxidative dehydrogenation of ethane. The catalyst was mounted in the apparatus of Figure 1, and an auto-thermal cracking reaction was carried out under the conditions summarized in Table 9 below.

Table 9

GHSV @ stp/h	119845
Ethane flow (g/min)	18.07
Hydrogen flow (g/min)	1.18
Oxygen flow (g/min)	9.39
Nitrogen flow(g/min)	4.56

5 Table 10 below shows the ethane conversion and ethylene selectivity of the reaction.

Table 10

Ethane conversion (%)	80.01
Ethylene selectivity (g ethylene per 100g ethane converted)	71.37

10

15


20

Claims

1. A process for the production of an olefin from a hydrocarbon, which process comprises:
partially combusting the hydrocarbon and an oxygen-containing gas in the presence of a catalyst, characterised in that the catalyst comprises palladium and at least one
5 further metal, said further metal being a Group IIIA, Group IVA, VA or a transition metal.
2. A process as claimed in claim 1, wherein the stoichiometric ratio of hydrocarbon to oxygen is 5 to 13.5 times the stoichiometric ratio of hydrocarbon to oxygen required for complete combustion of the hydrocarbon to carbon dioxide and water.
- 10 3. A process as claimed in claim 1 or claim 2, wherein said partial combustion of hydrogen and oxygen-containing gas is carried out in the presence of hydrogen.
4. A process as claimed in any preceding claim, wherein said catalyst comprises at least one further metal which is a Group IIIA metal.
5. A process as claimed in claim 4, wherein said Group IIIA metal is Al, Ga, In
15 and/or Tl.
6. A process as claimed in any preceding claim, wherein said catalyst comprises at least one further metal which is a Group IVA metal.
7. A process as claimed in claim 6, wherein said Group IVA metal is Ge, Sn and/or Pb.
- 20 8. A process as claimed in any preceding claim, wherein said catalyst comprises at least one further metal which is a Group VA metal.
9. A process as claimed in claim 9, wherein said Group VA metal is Sb and/or Bi.

10. A process as claimed in any preceding claim, wherein said catalyst comprises at least one further metal which is a transition metal.
11. A process as claimed in claim 10, wherein said transition metal is selected from the group consisting of Cr, Mo, W, Fe, Ru, Os, Co, Rh, Ir, Ni, Pt, Cu, Ag, Au, Zn, Cd and Hg.
12. A process as claimed in any preceding claim, wherein said catalyst comprises only one further metal selected from Group IIIA, Group IVA, VA and the transition metal series.
13. A process as claimed in any one of claims 1 to 11, wherein said catalyst comprises at least two further metals selected from Group IIIA, Group IVA, VA and the transition metal series.
14. A process as claimed in claim 13, wherein the catalyst comprises one metal selected from Groups IIIA, IVA and VA, and one metal selected from the transition metal series.
15. A process as claimed in claim 14, wherein said metal selected from the transition metal series is Pt.
16. A process as claimed in claim 14 or 15, wherein said one metal selected from Groups IIIA, IVA and VA is Sn.
17. A process as claimed in claim 13, wherein said catalyst comprises two metals selected from the transition metal series.
18. A process as claimed in claim 17, wherein said catalyst comprises Pd, Pt and Cu.
19. A process as claimed in any preceding claim, wherein said catalyst further comprises alkali metal ions.
20. A process as claimed in any preceding claim, wherein said hydrocarbon comprises at least one hydrocarbon selected from the group consisting of ethane, propane and butane.
21. A catalyst comprising a) palladium, b) a further transition metal and c) a metal from Group IIIA, IVA and/or VA.

1/1



Key : • Location of thermocouples

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 00/04813

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C07C5/48 B01J23/54

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 C07C B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 04632 A (BP CHEMICALS) 3 March 1994 (1994-03-03) claims	1,10-12, 20
X	US 4 788 371 A (IMAI ET AL) 29 November 1988 (1988-11-29) claims	1,4-7,20
X	US 3 437 703 A (REITMEIER R. E. ET AL) 8 April 1969 (1969-04-08) claims	1,10,11
P,X	WO 00 14037 A (THE DOW CHEMICAL COMPANY) 16 March 2000 (2000-03-16) claims	1,4-10
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

9 February 2001

Date of mailing of the international search report

16/02/2001

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Van Geyt, J

INTERNATIONAL SEARCH REPORT

Inter. Application No
PCT/GB 00/04813

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 29021 A (DEN NORSKE STATS OLJESELSKAP) 22 December 1994 (1994-12-22) claims ---	1,6,7
X	EP 0 602 864 A (JOHNSON MATTHEY PLC) 22 June 1994 (1994-06-22) claims ---	21
X	EP 0 478 144 A (STANDARD OIL CO OHIO) 1 April 1992 (1992-04-01) claims ---	21
X	EP 0 471 320 A (JAPAN HALON CO LTD) 19 February 1992 (1992-02-19) claims ---	21
X	FR 2 285 340 A (STAMICARBON) 16 April 1976 (1976-04-16) claims ---	21
X	US 4 638 085 A (BROECKER FRANZ J ET AL) 20 January 1987 (1987-01-20) claims ---	21
X	US 3 123 574 A (M. ZAJCEW) 3 March 1964 (1964-03-03) claims ---	21
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 01, 30 January 1998 (1998-01-30) -& JP 09 255626 A (MITSUBISHI RAYON CO LTD), 30 September 1997 (1997-09-30) abstract ---	21
X	PATENT ABSTRACTS OF JAPAN vol. 1997, no. 12, 25 December 1997 (1997-12-25) -& JP 09 221452 A (MITSUBISHI RAYON CO LTD), 26 August 1997 (1997-08-26) abstract -----	21

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 00/04813

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9404632 A	03-03-1994	AT 148914 T AU 4727193 A BG 99508 A BR 9306931 A CN 1090566 A CZ 9500373 A DE 69308145 D DE 69308145 T EP 0656044 A HR 931121 A HU 71164 A, B PL 307559 A RU 2115692 C SI 9300441 A SK 23195 A US 5625111 A ZA 9306019 A	15-02-1997 15-03-1994 31-01-1996 12-01-1999 10-08-1994 18-10-1995 27-03-1997 28-05-1997 07-06-1995 31-12-1994 28-11-1995 29-05-1995 20-07-1998 31-03-1994 11-07-1995 29-04-1997 17-02-1995
US 4788371 A	29-11-1988	CA 1292248 A DE 3879147 A DE 3879147 T EP 0323115 A ES 2053776 T JP 1252695 A JP 1712270 C JP 3077235 B	19-11-1991 15-04-1993 01-07-1993 05-07-1989 01-08-1994 09-10-1989 11-11-1992 09-12-1991
US 3437703 A	08-04-1969	DE 1618415 A NL 6706340 A	25-03-1971 06-11-1967
WO 0014037 A	16-03-2000	AU 5799999 A AU 6241699 A WO 0014035 A US 6166283 A	27-03-2000 27-03-2000 16-03-2000 26-12-2000
WO 9429021 A	22-12-1994	NO 932173 A AT 177971 T AU 7009094 A DE 69417416 D DE 69417416 T DK 705136 T EP 0705136 A ES 2128565 T NO 954943 A US 5922925 A US 5817596 A	15-12-1994 15-04-1999 03-01-1995 29-04-1999 11-11-1999 11-10-1999 10-04-1996 16-05-1999 06-12-1995 13-07-1999 06-10-1998
EP 0602864 A	22-06-1994	AT 185707 T AU 673018 B AU 5247393 A CA 2111528 A DE 69326820 D DE 69326820 T DK 602864 T ES 2137233 T GR 3032430 T JP 7313877 A US 5478528 A	15-11-1999 24-10-1996 30-06-1994 19-06-1994 25-11-1999 09-03-2000 25-04-2000 16-12-1999 31-05-2000 05-12-1995 26-12-1995

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 00/04813

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0478144 A	01-04-1992	US 5066809 A JP 4273858 A	19-11-1991 30-09-1992
EP 0471320 A	19-02-1992	JP 2763186 B JP 4099738 A DE 69109574 D DE 69109574 T US 5283379 A	11-06-1998 31-03-1992 14-06-1995 07-09-1995 01-02-1994
FR 2285340 A	16-04-1976	NL 7412507 A AR 205757 A AT 350501 B AT 727475 A AU 8501475 A BE 833710 A BR 7506114 A CH 614180 A CS 188127 B DE 2542421 A ES 441155 A GB 1515190 A IT 1047087 B JP 51059797 A TR 18845 A ZA 7505982 A	25-03-1976 31-05-1976 11-06-1979 15-11-1978 24-03-1977 23-03-1976 03-08-1976 15-11-1979 28-02-1979 01-04-1976 16-03-1977 21-06-1978 10-09-1980 25-05-1976 01-11-1977 25-08-1976
US 4638085 A	20-01-1987	DE 3210708 A CA 1190534 A DE 3367169 D EP 0089587 A JP 1757560 C JP 4046618 B JP 58166936 A	06-10-1983 16-07-1985 04-12-1986 28-09-1983 20-05-1993 30-07-1992 03-10-1983
US 3123574 A	03-03-1964	NONE	
JP 09255626 A	30-09-1997	NONE	
JP 09221452 A	26-08-1997	NONE	